



## TECHNICAL SPECIFICATIONS

ASTM F-1303 designation	Type I, Grade 1, Class B Back
ASTM F-1303* see test methods below	Pass
Surface Finish	PU
Overall Thickness	2.2 mm
Wear Layer Thickness	0.022"
Static Load ASTM F-970 *modified	1,400 PSI
Smoke ASTM E-662	Less than 450
Flame Spread ASTM E-648	Class 1, 0.45 cm2 or more

\* Test included in ASTM F-1303

ASTM F-137 Test Method for Flexibility of Resilient Flooring Materials with Cylindrical Mandrel Apparatus

ASTM F-386 Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces

ASTM F-410 Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement

ASTM F-925 Test Method for Resistance to Chemicals of Resilient Flooring

ASTM F-970 Test Method for Static Load Limit

ASTM F-1482 Practice for Installation and Preparation of Panel Type Underlayments to Receive Resilient Flooring

ASTM F-1514 Test Method for Measuring Heat Stability of Resilient Flooring by Color Change

ASTM F-1515 Test Method for Measuring Light Stability of Resilient Flooring by Color Change

ASTM F-1914 Test Methods for Short-Term Indentation