

LUXURY VINYL FLOORING

PLANKS

Collection	Standard Size	Gauge	Wear Layer	Texture	Finish	Additional Options Available
Astratto	7.25" x 48"	3mm	22 mil	Natural Stone	Urethane	2mm with 8 mil or 12 mil 7" x 48" Plank (2mm)
Chalet	7" x 48"	2mm	8 mil	Hand-Scraped	Urethane	2mm with 12 mil 3mm with 22 mil
Chevron	7.25" x 48"	3mm	22 mil	Emboss	Urethane	2mm with 8 mil or 12 mil
Classic	6" x 36"	3mm	22 mil	<i>Varies by SKU</i>	Urethane	2mm with 8 mil or 12 mil
Coastline	7.25" x 48"	3mm	22 mil	Smooth	Urethane	2mm with 8 mil or 12 mil 7" x 48" Plank (2mm)
Fresco	7.25" x 48"	3mm	22 mil	Smooth	Urethane	2mm with 8 mil or 12 mil 7" x 48" Plank (2mm)
Maplewood	7.25" x 48"	3mm	22 mil	Smooth	Urethane	2mm with 8 mil or 12 mil 7" x 48" Plank (2mm)
Ombre	6" x 48"	3mm	22 mil	Wood Grain	Urethane	2mm with 8 mil or 12 mil
Timber	6" x 36"	3mm	22 mil	<i>Varies by SKU</i>	Urethane	2mm with 8 mil or 12 mil
Zen	7" x 48"	2mm	8 mil	Smooth	Urethane	2mm with 12 mil 3mm with 22 mil (Plank 7.25" x 48")

TILES

Crete II	23.62" x 23.62"	3mm	22 mil	Concrete Emboss	Urethane	Please inquire for additional options
Grotto	18" x 36"	3mm	22 mil	Natural Stone	Urethane	Please inquire for additional options
Lake House	24" x 24"	3mm	22 mil	Registered Emboss	Urethane	
Linen II	18" x 18"	3mm	22 mil	Registered Emboss	Urethane	Please inquire for additional options
Sahara	18" x 36"	3mm	22 mil	Natural Stone	Urethane	Please inquire for additional options
Spectrum	23.62" x 23.62"	3mm	22 mil	Concrete	Urethane	Please inquire for additional options
Verona	18" x 36"	3mm	22 mil	Natural Stone	Urethane	Please inquire for additional options



FAST FACTS

- Do not stack material over 2 pallets.
- The permanent HVAC system must be on and maintained at a minimum of 68° F (20°C).
- LVT should only be installed directly over a solid structural subfloor such as concrete, plywood, or sealed/primed gypsum-based underlayment.
- When installing tiles, ensure all tiles are from the same batch/shade.
- It is essential that moisture tests be performed on all concrete sub-floors regardless of grade level or whether or not the concrete is freshly poured or is classified as an older slab. Moisture testing should be performed according to ASTM F 1869 Calcium Chloride Test with moisture levels not to exceed eight (8) pounds per Twenty-Four (24) hours per one thousand (1000) square feet or ASTM F 2170 In Situ Relative Humidity Test with moisture levels, relative humidity, when measured by this method, not to exceed ninety (90) percent. If the test results exceed the limitations, the installation should not proceed until the problem has been corrected. In addition to and not in lieu of the moisture test, perform the Adhesive Bond Test described in the next bullet point.

- Adhesive Bond Test: In several locations throughout the area to receive the flooring, glue down 3' x 3' pieces of the flooring with the adhesive. Allow to set for 72 hours. A sufficient amount of force should be required to remove the flooring. Additional information with regard to these tests and results can be obtained through FloorFolio Industries' Technical Service Department. Additional information with regard to sub-floor installation and requirements can be found in ASTM F-710. Conduct an adhesive bond test.
- Subfloor must be smooth, rigid, flat, level, permanently dry, clean and free of all foreign material such as dust, paint, grease, oils, solvents, curing and parting compounds, sealers and old adhesive residue.
- Use only cementitious patching and leveling compounds.
- If FloorFolio LVT is installed over a gypsum-based underlayment the subfloor must be primed and/or sealed according to the manufacturer of the gypsum based underlayment using the primer and/or sealer recommended by the underlayment manufacturer for use when using a resilient finished floor. If this step is not taken there will likely be a failure due to the carrier in the adhesive being absorbed in the gypsum-based underlayment.
- Suitability of the subfloor rests solely with the installer.
- All flooring materials and adhesive should be acclimated to the jobsite conditions for a minimum of 24 hours prior to beginning the installation.
- Install Lake House tiles (24" x 24"), Crete II, Linen II, and Spectrum tiles (23.62" x 23.62") by quarter-turning every other tile.
- Use 'FloorFolio 9100' Pressure Sensitive adhesive for 2mm LVT when longer open times are needed. Refer to label instructions for additional details.
- Use 'FloorFolio 9000' adhesive. For areas exposed to topical water, heavy rolling loads, and under Hill-Rom hospital beds, 'FloorFolio 9200' two part epoxy adhesive is recommended. When 'FloorFolio 9200' adhesive is used, patching and leveling compounds must be dry for 24 hours.
- Use a 3/64" x 3/64" x 3/64" U-notched trowel. Replace worn trowels, do not re-notch worn trowel.
- Roll material with a 100-150 pound roller.
- Avoid foot traffic and rolling loads for 24 hours after installation is complete.
- Follow adhesive label instructions regarding open time and working time.
- Consult FloorFolio Flooring installation manual for complete installation instructions.



Luxury Vinyl Flooring
 FAST FACTS – 2023
 (800) 671-1124
sales@floorfolio.com
floorfolio.com